

In the Claims:

Please amend the claims as follows:

1. (Currently Amended) A method of making a master for manufacturing an optical disc comprising:

an exposing step of applying a laser beam for recording modulated by an information signal corresponding to an information signal of an information concave and convex pattern formed on said optical disc to an inorganic resist layer formed on a substrate to form an exposed pattern corresponding to said information concave and convex pattern of said optical disc, and

after the preceding step a developing step of performing development processing on said inorganic resist layer to form a concave and convex pattern corresponding to said information exposed concave and convex pattern of said inorganic resist layer, wherein

in said exposing step, a laser beam for estimation is applied to a predetermined area on said inorganic resist layer to estimate information signal characteristics of said exposed pattern of said inorganic resist layer using reflected light of the laser beam for estimation, and power of said laser beam for recording is controlled based on the estimated result.

2. (Original) A method of making a master for manufacturing an optical disc according to claim 2, wherein said inorganic resist layer is a resist layer containing an incomplete oxide of transition metals.

3. (Original) A method of making a master for manufacturing an optical disc according to claim 1, wherein a predetermined area irradiated with said laser beam for estimation is an area other than the area irradiated with the laser beam for recording on the inorganic resist layer.

4. (Original) A method of making a master for manufacturing an optical disc according to claim 1, wherein while said laser beam for recording is being applied, said laser beam for estimation is applied to the proximity of the position irradiated with said laser beam for recording.

5. (Original) A method of making a master for manufacturing an optical disc according to claim 1, wherein said laser beam for estimation irradiated with said laser beam for recording being irradiated is applied to an unexposed area and exposed area with respect to said laser beam for recording in the proximity of the irradiated position with said laser beam for recording, and the information signal characteristics of said exposed pattern of said inorganic resist layer are estimated using a ratio between reflected light amount from said unexposed area and reflected light amount from said exposed area, with said laser beam for estimation.

6. (Original) A method of making a master for manufacturing an optical disc according to claim 5, wherein power of said laser beam for recording is controlled so that said ratio between reflected light amounts is constant.

7. (Currently Amended) A method of manufacturing an optical disc comprising the steps of: making a master for manufacturing the optical disc, making a stamper for manufacturing said optical disc from said master by transfer, manufacturing an optical disc substrate by transfer using said stamper, depositing a reflective film on the optical disc substrate, and depositing a protective film, wherein

the step of making said master includes: an exposing step of applying a laser beam for recording modulated by an information signal corresponding to an information signal of an information concave and convex pattern formed on said optical disc to an inorganic resist layer formed on the substrate to form an exposed pattern corresponding to the information concave and convex pattern on said optical disc, and after the preceding process a step of performing development processing to said inorganic resist layer to form a concave and convex pattern corresponding to said information ~~exposed~~ concave and convex pattern of said inorganic resist layer; and in said exposing step, a laser beam for estimation is applied to a predetermined area on said inorganic resist layer to estimate information signal characteristics of said exposed pattern by said inorganic resist layer from reflected light of the laser beam for estimation, and based on the estimated result, power of said laser beam for recording is controlled.

8. A method of manufacturing an optical disc according to claim 7, wherein said inorganic resist layer is a resist layer containing an incomplete oxide of transition metals.